



H+H UK Limited, Ightham, Sevenoaks, TN15 9HZ

13

HHUK-010

**EN 998-2
Celfix Thin layer Mortar**

Designed masonry mortar for use in aircrete thin layer masonry in elements subject to structural requirements

Compressive strength: M10

Initial Shear Strength: 0.30 N/mm² (tabulated Value)

Contents of chloride: Less than 0.1%

Density: 1400±150kg/m³

Reaction to fire: Euroclass A1

Water absorption: NPD

Workable Life: Not less than 2 hours

Correction Time: Not less than 6 minutes

Maximum Grain Size: 2mm

Water vapour permeability μ : 5/20 (tabulated value)

Thermal conductivity: ($\lambda_{10, dry}$) 0.45 W/mK (tabulated value)

Durability: For use above and below ground level.